



Elastospray 0962-025U

POLYURETHANE SPRAY FOAM ADHESIVE SYSTEM

A two-component (Part A and B) polyurethane low-rise adhesive for bonding insulation to approved, compatible substrates. Consult Product Data Sheets for additional information.

Notes:

1. Requires heated, high-pressure proportioning spray equipment. Consult BASF for details.
2. Adhesive must be applied as a continuous layer.
3. Lay insulation into adhesive and maintain even, uniform pressure across the board.
4. Storage temperatures in excess of 90°F (32°C) may affect shelf life.
5. If exposed to temperatures below 40°F (5°C) restore to a minimum temperature of 60°F (15°C) before use.
6. Job site conditions may affect performance. BASF Elastospray 0962-025U adhesive shall not be used if surface and/or ambient temperatures below 40°F (5°C) are expected during application or subsequent curing time.
7. The addition of a Catalyst to Part B may be required when temperatures are between 40°F (5°C) and 60°F (27°C).
8. Adhesive shall not be applied to: wet or damp surfaces, contaminated or dirty surfaces.

APPLICATION RATES FOR INSULATION		
	Approximate Sq. Ft. per Drum Set	
	50 Gal. (950 lb) Set	15 Gal. (265 lb) Set
Wood	8,500 - 9,000	2,500 - 2,700
Concrete	8,500 - 9,000	2,500 - 2,700
Smooth Gypsum	8,500 - 9,000	2,500 - 2,700
Cellular Concrete (consult Technical Dept.)	8,500 - 9,000	2,500 - 2,700
Cementitious Wood Fiber	7,500 - 8,000	2,250 - 2,400
Isocyanurate Board with Facer	8,500 - 9,000	2,500 - 2,700
Mineral Cap Sheet	8,500 - 9,000	2,500 - 2,700
Gravel B.U.R. (Clean)	5,000 - 7,000	1,500 - 2,100
Smooth B.U.R./Mod. Bit.	8,500 - 9,000	2,500 - 2,700